

Screen Goo Projection Screen Coatings



Max Contrast Reflective Coating

<u>Description</u>	<u>Characteristics</u>	<u>Specifications</u>
<p>Screen Goo Max Contrast Reflective Coating is the reflective component of the Screen Goo two part video projection screen system; to be used in conjunction with Screen Goo Max, Max+20, Ultra Max, Ultra Max+20, Ultra Silver 3D and High Extinction 3D Finish Coatings.</p> <p>Advantages</p> <ul style="list-style-type: none"> – ASTM D4236 approved non-toxic water base acrylic coating – ASTM E-84-06 approved for fire safety – No California Proposition 65 Statement required – VOC: 80g/1000mL (per ASTM D3960 method) – lead-free – premium, colour fast pigments – museum grade 100 % acrylic base – very durable – very matte – very reflective – not degraded by UV light – strongly resistant to yellowing – spray or roller application – suitable for indoor and outdoor use 	<p>Gloss: N/A intended for use as an undercoat</p> <p>Volume Solids: 36.5-38.5</p> <p>Viscosity: 55 seconds # 5 Zahn cup</p> <p>Recommended film thickness: Mils Wet: 1.5 Mils Dry: 0.50</p> <p>Spreading Rate (no application loss): 378 sq. ft. /gal @ (recommended Mils Dry Film Thickness)</p> <p>Drying (25° C/77°F; 45% RH): To Touch: 1 hour To Handle: 24 hrs. To Sand: 48 hrs. To Recoat: 1 hour Force Dry: not recommended Curing temperature should not exceed 40°C/104°F</p> <p>Mixing Ratio: N/A</p> <p>Pot Life: N/A</p> <p>Flash Point: will not ignite; may boil at > 100°C/212°F</p> <p>Package Life: 5 years unopened</p>	<p>General: Substrate should be free of grease, oil, dirt, fingerprints and other contaminants.</p> <p>Drywall: Minimum level 4 finish recommended. Prime with 100% acrylic water base or urethane modified acrylic primers only.</p> <p>Wood Products: Prime with quality white primer compatible with water based over-coating.</p> <p>Fabrics: Will adhere correctly and permanently to all natural fibre materials: canvas, muslin, etc. Not recommended for application to PVC, polyester and any substrate containing solvents or volatile plasticizers.</p>
		<p><u>Application Notes</u></p> <p><u>Two coat application required</u></p> <p>Rolled: Use maximum 1/4" nap, lint-free rollers; foam rollers are not recommended.</p> <p>Sprayed: Use an HVLP system for application <50 sq. ft.; 1.5-2mm tip diameter. 40-45 psi. For applications > 50sq. ft., use industrial capacity airless systems.</p>

