# **Screen Goo Projection Screen Coatings**



## **Rear Projection Coating**

### **Description**

Screen Goo Rear Projection Coating is a semi-translucent diffusive coating intended for application to transparent substrates for the creation of double-sided rear projection surfaces

#### Advantages

- ASTM D4236 approved non-toxic water base acrylic coating
- ASTM E-84-06 approved for fire safety
- No California Proposition65 Statement required
- VOC: 89g/1000mL (per ASTM D3960 method)
- lead-free
- premium, colour fast pigments
- museum grade 100 % acrylic base
- very durable
- polarity preserving
- very reflective
- not degraded by UV light
- strongly resistant to yellowing
- spray application only
- suitable for indoor and outdoor use

### **Characteristics**

Gloss: 15

Volume Solids: 36.5-38.5 Viscosity: 18 seconds # 3 Zahn

cup

**Recommended film thickness:** 

Mils Wet: 1.5 Mils Dry: 0.50

**Spreading Rate** (no application loss): 302.4 sq. ft. /gal @ (recommended Mils Dry Film

Thickness)

**Drying** (25° C/77°F; 45% RH):

To Touch: 1 hour To Handle: 24 hrs.

To Sand: not recommended

To Re-coat: 4 hours

Force Dry: not recommended Curing temperature should not

exceed 40°C/104°F Mixing Ratio: N/A Pot Life: N/A

Flash Point: will not ignite; may

boil at > 100°C/212°F

Package Life: 5 years unopened



#### **Specifications**

**General:** Substrate should be free of grease, oil, dirt, fingerprints and other contaminants.

**Drywall:** Level 5 finish required. Prime with 100% acrylic water base or urethane modified acrylic primers only.

Wood Products: Level 5 finish required. Prime with quality white primer compatible with water based over-coating.

Fabrics: Will adhere correctly and permanently to all natural fibre materials: canvas, muslin, etc. Not recommended for application to PVC, polyester and any substrate containing solvents or volatile plasticizers.

#### **Application Notes**

# Two or more coat application required

**Rolled:** not recommended.

**Sprayed:** Use an HVLP system for application <50 sq. ft.; 1.5-2mm tip diameter. 40-45 psi. For applications > 50sq. ft., use industrial capacity airless system: 12 -14 fan spray tip; piston pump; maximum 50 ft. of hose; <sup>3</sup>/<sub>4</sub> gpm capacity. Still air required for best results, minimize air circulation while applying.